
Melamineby OCITM GPH Product Specifications



CAS No.: 108-78-1 EINEC No.: 203-615-4

Formula C3H6N6

Synonyms: 2,4,6-triamino-1,3,5-triazine

Molecular Weight 126.13 g/mol

Appearance White, crystalline powder

Properties	Specifications units	Test method
Melamine	Min. 99.8 %	MSC-TIS 002
Water	Max. 0.1 %	MSC-TIS 174
Ash	Max. 0.01 %	MSC-TIS 001
Iron	Max. 1 mg/kg	MSC-TIS 004
Clarity*	Clear	MSC-TIS 010
Color*	Max. 20 APHA	MSC-TIS 014

Safety precautions

Melamine is non-flammable, but heating to above 300°C could result in decomposition, with release of toxic vapors. Adequate ventilation and the use of personal protective equipment is therefore advised. When handling melamine, the wearing of gloves, safety glasses and respiratory protection is recommended.

The above data is only given as a guide. It does not replace our Material Safety Data Sheet (available on request), which contains additional detailed information.

Testing

Details of OCI test methods are available on request.

Contact

OCI Melamine Europe P.O. Box 601, 6160 AP Sittard

The Netherlands

Phone: +31 46 702 0203 Fax: +31 46 702 0192

E-mail: info.melamine@ocinitrogen.com Internet: www.ocimelamine.com

PT. OCI KALTIM Melamine Gedung Tetra Pak Lantai 2 Jl. Buncit Raya Kay. 100

Jakarta 12510 Indonesia

Edition: July 1, 2010

Phone: +62 21 798 4261 Fax: +62 21 798 4266 OCI Melamine Americas, Inc.

C/o Advanced Louisiana Logistics, (ALL)

320 Somerulos Street Suite 217

Baton Rouge, LA 70802

USA

Phone: +1 225 685 3020 Fax: +1 225 685 3003

OCI Melamine China Ltd

17N, Feizhou Guoji Building, No.899 Lingling Road, Shanghai 200030

China

Phone: +86 021 6441 5436 Fax: +86 021 6441 5440

All data, suggestions and information supplied by or on behalf of OCI with respect to its products are based on research and deemed to be reliable. However, since OCI has no influence on the use, processing and application of the same, OCI can accept no responsibility whatsoever in this respect. Health & Safety-related information has been provided in conjunction with this information in a separate document and must be considered in the handling and use of this product. The buyer shall check the quality and all other properties of the product, and assumes all responsibilities arising from the use of the products and the information related thereto. OCI accepts no liability ensuing from the use, misuse, or other activities related to any further processing of this product or any infringement of rights to trademarks, patents, etc., owned or controlled by third parties that are the result of manufacturing, application or sale of products by the buyer.

OCI MELAMINE